



6859 Renoir Avenue  
Baton Rouge, LA 70806

Tel: (225) 924-3221  
Fax: (225) 927-2918

## LEWCO 10 x 10 Fiberglass Scrim

Style 1769/1671

---

### Product Specifications

Weave	LENO*
Thread	10 x 10
Weight	1.4-1.8 Oz./Sq. Yd.
Thickness	.0070 ±10% Inches
Warp Yarn	ECG 150 1/0 18
Fill Yarn	ECG 75 x 1/0 9
Breaking Strength	60 *60
Width	3" Inches
Put-Up	50 Yard Rolls
Specifications	Meets ASTM D 1668-80 Type III (ASTM 579)

\*\*\*SBR (Styrene Butadiene Rubber) Finish which is resin Compatible with\*\*\*  
\*\*\*asphalt base or tar base compounds\*\*\*

\*\*\*SBR Finish will burn off at 325°F. The glass yarns start to soften at 1560°F\*\*\*  
\*\*\*(849° C). AT 2800°F, the glass yarns begin to get brittle.\*\*\*

---

### **\*LENO Weave results in a 10 x 10 Visual Count**

This information is given in good faith and is believed to be accurate. All liabilities are borne by the user of this product. LEWCO does not take any responsibility for misuse of this product. LEWCO recommends testing before use.

S1010SCRIM-06/09/04MED