



6859 Renoir Avenue  
Baton Rouge, LA 70806

Tel: (225) 924-3221  
Fax: (225) 927-2918

## LEWCO 2025-9383 H-I Heat Treated Fiberglass Fabric

LEWCO Style 2025-9383 H-I is an asbestos free woven fiberglass fabric, heat treated to set the weave and eliminate organic binders. LEWCO Style 2025-9383 H-I is a very soft, flexible fabric for pipe lagging, removable insulation blankets, and fire blankets. This material fire resistance meets the requirements for incombustibility as specified by the US Coast Guard 164.009. This material has been tested and meets NFPA 701-1999 Fire Tests for Flame-Resistant Textiles and Films Method 1.

		<u>Test Method</u>
Base Cloth	Heat Treated Fiberglass	
Weight	18.0 Oz./Sq.Yd. (+/- 10%)	ASTM D-3776-96
Thickness	.032 Inches	ASTM D-1777-96
Construction	20 x 14 W F	
Tensile Strength	200 Lb. x 150 Lb. W F	ASTM D-5034-95
Temperature Resistance Continuous	1100 ° F	
Temperature Resistance Melt Point	1523 ° F	
Weave	Plain	
Width	40" & 60"	

This information is given in good faith and is believed to be accurate. It is intended for use by persons skilled in the art of fabricating and applying removable/reusable insulation or like products. All liabilities are borne by the user. LEWCO takes no responsibility for misuse of this product. LEWCO recommends testing before use.

S9383HI-10152015MH